

# FLAMMADUR® A 365

## Two-component casting resin

### Description

FLAMMADUR® A 365 is a black two-component polyurethane casting resin that forms an insulating layer. It is suitable for the production of cable penetrations, elastic panels and moulded parts for preventive fire protection.

### Areas of Application

- Cable management
- Rolling stock
- Ships & offshore
- On request



### Delivery and Packaging

FLAMMADUR® A 365				
Packaging	tin	drum	sep. hardener	
Size	1 kg	250 kg	5 kg	25 kg
<b>Article number</b>				
	4146389	4146289	4146348	4145953

Please contact us for further information:

☎ +49 4105-40 90-14

✉ [transportation@svt.de](mailto:transportation@svt.de)

**FLAMMADUR®  
A 365**

Protect your values.



members of svt group

AIK

FLAMRO

ROLFKUHNGBMH

**Technical Data**

	FLAMMADUR® A 365 (resin)	FLAMMADUR® A 365 (hardener)
Mixing ratio (parts by weight)	100	12
Mixing ratio (parts by volume)	7.0	1.0
Viscosity	approx. 25 000 mPa·s	approx. 40 mPa·s
Viscosity of the mixture	~ 9000 mPa·s	
Density	1.46 kg/l	1.22 kg/l
Mixing density	1.45 kg/l	
Pot life Bookfield RVT, +23 °C	4–30 min (adjustable)	
Curing time	3–24 hrs	
Flashpoint	> 200 °C	> 200 °C
Processing information	<ul style="list-style-type: none"> <li>The surfaces being cast must be dry and clean.</li> <li>Tools for the production of moulded parts must be provided with a suitable release agent.</li> <li>Processing is preferably carried out in a casting process with two-component dosing systems or by manual casting.</li> <li>FLAMMADUR® A 365 is insensitive to moisture and largely resistant to common technical oils and weak/diluted acids and alkalis.</li> </ul>	
Processing (min. +5 °C / < 90 % relative humidity)	With manual casting, the processing time at +23 °C between 4–30 minutes, the curing time is 3–24 hours. The pot life and curing times are adjustable and depend on the temperature	
Storage	Max. 6 months in the original unopened container. Protect from frost.	
Safety instructions	FLAMMADUR® A 365 is fibre and solvent free and not subject to any dangerous goods class. Consult the safety data sheet for additional instructions.	

**Moulding material**

Shore hardness (DIN 53505)	88–92 Shore A; 32–35 Shore D
Expansion pressure (300 °C) method A, sample thickness 5 mm, Ø 70 mm (DIBt guidelines, 1996)	0.6–1.2 N/mm²
Expansion (450 °C)	17 to 26 times
Application temperature range	-50 °C to +80 °C

Classification	The product meets the requirements R1 for hazard levels HL1–HL3 as per DIN EN 45545-2 (02/2016) DMT PB Nr. 8116069434-20 The product meets the requirements R17 for hazard levels HL2 DIN EN 45545-2 (02/2016) DMT PB Nr. 8116069434-20 The product meets the requirements according to DIN 5510:Teil 2 (05/2009) Exova PB-Nr. 2016-2003
----------------	------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

Errors, misprints and changes reserved. All of the information corresponds to the state of technology and the version of the standard that existed at the time of printing 11/2022  
 We will gladly provide you with information on request regarding the legal and technical framework conditions or manufacturer specifications applicable to your individual case.  
 © Copyright svt Products GmbH, Seevetal. FLAMMADUR® is a registered trademark ® of svt Products GmbH, Seevetal.

Technical product data sheet Rev: 1.1